

15-Oct-09

To: Mino Tech Engineering Inc.

Asahi Glass Co.,Ltd.
1-12 Yurakucho 1Chome
Chiyoda-ku,Tokyo, JAPAN
TEL: 81-3-3218-5433
FAX: 81-3-3218-7861

Certificate of Quality

Frit Type : DT430
Frit Code : W2521A
Lot No. : 081203
Q'TY : 1kg

- Characteristics -

Characteristics	Inspection data	specification
Diameter of Flow button (430°C-10min)	24.1 mm	
Residual Stress (On plate glass 430°C-10min)	+107 kg/cm ²	
Average diameter of particle	5.5 μm	
DTA Transition point	310 °C	
DTA Softening point	353 °C	

Asahi Glass Co.,LTD.

M.Satoh

電子署名者: M_Satoh
DN: cn=M_Satoh, o=JP - 日本, ou=AGC
Electronics Co.,Ltd., ou=Quality
Assurance Group, Pri Paste Div.,
email=m.satoh@agc.co.jp
日付: 2009.10.14 09:46:28 +0900

N_Katsumi

電子署名者: N_Katsumi
DN: cn=N_Katsumi, o=AGC Electronics
Co.,Ltd., ou=Quality Assurance Group,
email=tenobuya-katsumi@agc.co.jp, cn=JP
日本
日付: 2009.10.14 10:12:35 +0900